

## **POROFILZ<sup>®</sup> ME 2070, 2074**

Description:

Highly absorbent and soft PET-felt containing an accelerator. ME 2070 contains additional an accelerator for epoxy acid anhydride hardener system.

Properties:

POROFILZ<sup>®</sup> ME 2070, 2074 is highly absorbent, soft and compressible.

Application:

POROFILZ<sup>®</sup> ME 2070/2074 can be used in VPI-systems as interlayer spacer and filling material which is capable of a 600 % resin pickup.

Materials:

POROFILZ<sup>®</sup> ME 2070 is a highly absorbent polyester felt containing a suitable accelerator based on a metallic salt for epoxy-anhydride impregnating resins.

POROFILZ<sup>®</sup> 2074 is a highly absorbend polyester felt without accelerator.

Formats:

Rolls: Nominal thickness 1.5 mm: max. 1000 mm width Nominal thickness 1.0 mm: max. 750 mm width Nominal thickness 2.0 mm: max. 950 mm width

· ·······					
Properties	Test method	Unit	Value	Value	Value
Nominal thickness		mm	1.0	2.0	1.5
Total substance	DIN 53854	g/m²	77 ± 27	313 ± 35	300 ± 30
PET-felt	DIN 53854	g/m²	70 ± 20	300 ± 30	300 ± 30
Binder	IPV Nr. 18	g/m²	7 ± 3	13 ± 5	-
Accelerator content	IPV Nr. 19	mgZn/m²	800 ± 300	1500 ± 600	-

Page 1 of 2 E POROFILZ ME 2070,2074 Created on 15/11/2004 All information given here is based on currently available facts and on the results of experiments performed with all due care in our laboratories. It does not in any way reduce the responsibility of the user for carrying out further tests in order to ensure successful processing and use in specific applications. ISOVOLTA AG A-2355 Wiener Neudorf Phone: +43/2236/605-0 Fax: +43/2236/605-477 electrical-insulation@isovolta.com www.isovolta.com

A Constantia Iso AG company



Page 2 of 2 E POROFILZ ME 2070,2074 Created on 15/11/2004 All information given here is based on currently available facts and on the results of experiments performed with all due care in our laboratories. It does not in any way reduce the responsibility of the user for carrying out further tests in order to ensure successful processing and use in specific applications. ISOVOLTA AG A-2355 Wiener Neudorf Phone: +43/2236/605-0 Fax: +43/2236/605-477 electrical-insulation@isovolta.com www.isovolta.com

A Constantia Iso AG company