

Normtabelle für Schichtpressstoffe auf Zellulosebasis mit Phenolharz

Vergleichbare Normen mit IEC 60893 (= DIN EN 60893/VDE 0318)							
IEC 60893	PF CP 201	PF CP 202	PF CP 206	PF CP 204	PF CC 201	PF CC 202	PF CC 203
DIN 7735	Hp 2061	Hp 2061.5	Hp 2062.8	Hp 2063	Hgw 2082	Hgw 2082.5	Hgw 2083
NEMA LI 1	X, XP	-	XXP	XXXP	C	CE	L
BS 2572	P1	-	P3	P4	F2	F4	F1
JIS K6912 >3mm	PL-PM	-	PL-PEM	PL-PEV	PL-FCM	PL-FCE	PL-FLI
JIS K6912 <3mm	PL-P-P	-	PL-PES-P	PL-PEV	-	-	-
ISOVOLTA VOLTIS®	Hp 2061	Hp 2061.5	Hp 2015D/2062.8	Hp 1015H/2063W	Hgw 2082	Hgw 2082.5 CE	Hgw 2083
ISOVOLTA VOLTIS®			Hp P1015D/2062.8				

Normtabelle für Schichtpressstoffe auf Glasfaserbasis

Vergleichbare Normen mit IEC 60893 (= DIN EN 60893/VDE 0318)										
IEC 60893	EP GC 201	EP GC 202	EP GC 203	EP GC 204	EP GC 205	EP GC 306	EP GC 308	UP GM 201	SI GC 202	PF GC 201
DIN 7735	Hgw 2372	Hgw 2372.1	Hgw 2372.4	Hgw 2372.2	Hgw 2370.4	-	-	Hm 2472	Hgw 2572	Hgw 2072
NEMA LI 1	G 10	FR 4	G 11	FR 5	-	-	-	GPO 1	G 7	G 3
BS 3953	EP-3	EP-4	EP-5	EP-6	-	-	EP-7	-	SI 5	-
JIS K 6912	EL-GEM	EL-GEF	EL-GEH	EL-GEHF	(EL-GEH)	-	-	T-GEM	SL-GSE	PL-GH
ISOVOLTA ISOVAL®	A	FR4-HF	11	FR5-HF	R	11 HKB	11	VOLTIS® UP	VOLTIS® SI	VOLTIS® Hgw 2072
ISOVOLTA ISOVAL®	10	RKB-FR	TM				11 HKB			
ISOVOLTA ISOVAL®	10R (ähnlich)						TM			